

DECLARATION OF PERFORMANCE	
Reference :	DOPFibrabelMRFNAFv1
Commercial name :	Fibrabel MR FR NAF
Product type :	MDF Fibreboard
Reference standard :	Wood Based Panel - EN13986:2004+A1:2015 Annex A Table A.9
CE Class :	L-MDF H FR
Field of application :	Internal use as non-structural component in humid conditions
AVCP Class :	1
Certification number:	1161-CPR-1415 [12-25mm]
Produced at:	Rue de la Forêt 2, B-6690 Vielsalm

Essential Characteristic	Unit	Reference	Thickness range (mm)					
			6	>6 - 9	> 9 - 12	>=12-19	>19-30	>30-45
Bending strength	N/mm ²	EN 622-5	NPD	NPD	NPD	18	16	NPD
Modulus of elasticity in bending	N/mm ²	EN 622-5	NPD	NPD	NPD	1600	1500	NPD
Internal bond	N/mm ²	EN 622-5	NPD	NPD	NPD	0,45	0,45	NPD
Swelling in thickness, 24h	%	EN 622-5	NPD	NPD	NPD	13	12	NPD
Moisture resistance OPTION 1 : Internal bond	N/mm ²	EN 622-5	NPD	NPD	NPD	0,2	0,15	NPD
Moisture resistance OPTION 1 : Swelling in thickness	%	EN 622-5	NPD	NPD	NPD	15	15	NPD
Surface Soundness	N/mm ²	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Formaldehyde class	Class	EN 13986-table B1	NPD	NPD	NPD	E1	E1	NPD
Reaction to fire	Class	EN 13501-1	NPD	NPD	NPD	B-s1d0	B-s1d0	NPD
Water vapour permeability μ	wet dry	EN 13986 - table 9	NPD	NPD	NPD	20	20	NPD
Airborne sound insulation	dB	EN 13986-5.10	NPD	NPD	NPD	NPD	NPD	NPD
Sound absorption α		EN 13986 - table 10	NPD	NPD	NPD	0,10/0,20	0,10/0,20	NPD
Thermal conductivity λ	W/m.K	EN 13986 - table 11	NPD	NPD	NPD	0,1	0,1	NPD
Strength - tension ft	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - compression fc	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - bending f_m	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - panel shear f_v	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - planar shear f_r	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - tension E_t	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - compression E_c	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - bending E_m	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - panel shear G_v	N/mm ²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Impact resistance	Class	EN 12871	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength R_{mean}	N/mm ²	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength $F_{ser,k}$	N/mm ²	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength $F_{max,k}$	N/mm ²	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Linear expansion $\delta_{30,85}$	mm/m	EN 318	NPD	NPD	NPD	NPD	NPD	NPD
Mechanical durability (kmod; kdef)		Shall be taken from :	NPD	NPD	NPD	NPD	NPD	NPD
Biological durability	Service Class	EN 335	NPD	NPD	NPD	1	1	NPD
Content of PCP	ppm	EN 13986-5.18	NPD	NPD	NPD	<5	<5	NPD

Informative Characteristic	Unit	Reference	Thickness range (mm)					
			6	>6 - 9	> 9 - 12	>=12-19	>19-30	>30-45
Formaldehyde class	Class	ASTM E1333	CARB NAF < 0.04 ppm [12 -> 25mm]					
Moisture resistance class	Class	ANSI A208.2-2016	Class 115 [12 -> 25mm]					
Reaction to fire	Class	ASTM E84	Class 1/A [12 -> 25mm]					

Version date :
6/05/2019

Lode De Boe,
President UNILIN bvba, division panels



Tabella disponibilità: MDF HydroPure

Formato (mm)	Spessore (mm)		
	12	16	19
3050x1220		●	●

- *Spessori e formati possono variare a seconda della disponibilità*